DT01 Rec'd PCT/PT 2 3 DEC 2004

U.S. National Stage of PCT/JP03/08024 PRELIMINARY AMENDMENT

IN THE CLAIMS:

- 1. (Canceled)
- 2. (currently amended) A negative electrode for a rechargeable lithium battery which includes a conductive metal foil current collector and an active material layer provided on a surface of the current collector and comprising a binder and particles of active material containing silicon and/or a silicon alloy;

said negative electrode characterized in that said current collector has mechanical properties of at least 80 N/mm² tensile strength, at least 30 N/mm² proportional limit, at least 1.0 % elongation at break and at least 0.03 % elastic elongation limit and said binder has mechanical properties of at least 50 N/mm² tensile strength, at least 10 % elongation at break, at least 2.5 x 10^{-3} J/mm³ strain energy density and up to 10,000 N/mm² elastic modulus;

after provision of said active material layer on the surface of said current collector, heat treatment being carried out at a temperature higher than a glass transition temperature of said binder to improve adhesion of the binder to the current collector.

3. (currently amended) The negative electrode for a

4

U.S. National Stage of PCT/JP03/08024 PRELIMINARY AMENDMENT

PATENT

rechargeable lithium battery as recited in claim 2, characterized in that said negative electrode is obtained by providing said active material layer on the surface of said current collector and then carrying out a sintering treatment, and that said mechanical properties are imparted to the current collector by a thermal history of the sintering treatment.

- 4. (original) The negative electrode for a rechargeable lithium battery as recited in claim 2, characterized in that said mechanical properties are imparted to said current collector by subjecting the current collector to a heat treatment before said active material layer is provided on the surface of the current collector.
- 5. (currently amended) The negative electrode for a rechargeable lithium battery as recited in any one of claims 1-4 claim 2, characterized in that a thickness X of said active material layer, a thickness Y and a surface roughness Ra of said current collector satisfy the relationships $5Y \ge X$ and $250Ra \ge X$.
- 6. (currently amended) The negative electrode for a rechargeable lithium battery as recited in any one of claims 1 5

- claim 2, characterized in that said surface of the current collector that carries the active material layer thereon has a surface roughness Ra of at least 0.2 μm .
- 7. (currently amended) The negative electrode for a rechargeable lithium battery as recited in any one of claims 1 6 claim 2, characterized in that said current collector comprises a copper foil, a copper alloy foil or a metal foil having a copper or copper alloy surface layer.
- 8. (currently amended) The negative electrode for a rechargeable lithium battery as recited in $\frac{1}{2}$ and $\frac{1}{2}$ characterized in that said current collector comprises an electrolytic copper foil, an electrolytic copper alloy foil or a metal foil having an electrolytic copper or copper alloy surface layer.

9 - 10. (canceled)

11. (currently amended) The negative electrode for a rechargeable lithium battery as recited in claim 9 or 10 claim 2, characterized in that said sintering treatment is carried out at a

temperature lower than a decomposition temperature of said binder.

12. (canceled)

- 13. (currently amended) The negative electrode for a rechargeable lithium battery as recited in claim 12 claim 2, characterized in that said binder has said mechanical properties after a thermal history of said heat treatment.
- 14. (currently amended) The negative electrode for a rechargeable lithium battery as recited in any one of claims 1-13 claim 2, characterized in that said binder has a linear expansion coefficient of $0.1 \times 10^{-5} 30 \times 10^{-5}$ °C⁻¹.
- 15. (currently amended) The negative electrode for a rechargeable lithium battery as recited in any one of claims 1-14 claim 2, characterized in that said binder has a glass transition temperature of up to 450 °C.

16. (canceled)

17. (currently amended) The negative electrode for a

rechargeable lithium battery as recited in $\frac{1}{2}$ and $\frac{1}{2}$ characterized in that said binder comprises polyimide.

18 - 19. (canceled)

- 20. (currently amended) The negative electrode for a rechargeable lithium battery as recited in any one of claims 1-19 claim 2, characterized in that said active material particles have a mean particle diameter of up to 10 μ m.
- 21. (currently amended) The negative electrode for a rechargeable lithium battery as recited in any one of claims 1 20 claim 2, characterized in that said active material layer includes a conductive powder.
- 22. (currently amended) A rechargeable lithium battery including the negative electrode as recited in any one of claims 1

 21 claim 2, a positive electrode containing a positive electrode material and a nonaqueous electrolyte.